



RSJ SHARK

I N F O T E S T		Data/Ora:	01/02/2010 17.13
Temperatura :	22.5	Operatore :	Garlando
IDENTIFICAZIONE CAMPIONE		Fabbricante :	SHARK
		Mat. assorb. :	
Standard :	E2205	Densità :	
Vel. Min [m/s]:	7.50	Taglia Casco :	L
Picco Max [g]:	275	Massa Casco :	
HIC Massimo :	2400	Colore Casco :	

File	Est.	Modello Casco	Ca. N#	Cond.	Alt. [cm]	Taglia Fals.	Punto Imp.	Forma Incud.	Vel. [m/s]	Picco [g]	HIC
RSJ shark	021	RSJ	10-0420	-20	308	60	B	PIA	7,59	254	1538
RSJ shark	022	RSJ	10-0420	-20	308	60	x	PIA	7,65	243	1937
RSJ shark	023	RSJ	10-0420	-20	308	60	P	PIA	7,65	209	1922
RSJ shark	024	RSJ	10-0420	-20	308	60	R	PIA	7,59	181	1405

RISULTATI TEST IMPATTO

